

MasterTop® 1841 SRS CF

Methacrylate-based, self-leveling, flexible flooring system with decorative flake broadcast.

FORMERLY DEGAFLEX™ CF

YIELD

Primer: MasterTop SRS 41P with MasterTop SRS 103IN - 100 ft² (9.3 m²)/batch
Self-Leveling Body Coat: MasterTop SRS 40TC - 40 ft² (3.71 m²) batch @ 1/8" (3.2 mm)
Top Coat: MasterTop SRS 71TC 100 ft² (9.3 m²) / batch
Flake Blend: MasterTop DE 111FK 6.54 ft² / pound (1.34 m²/kg)
All coverage rates are approximate. Coverage rates will vary with the desired texture and porosity of substrate.

PACKAGING

MasterTop SRS 41P: 4.5 gallon (17 L) pail, 49 gallon (185 L) drum
MasterTop SRS 40TC: 4.5 gallon (17 L) pail, 53.5 gallon (202.5 L) drum
MasterTop SRS 71TC: 4.5 gallon (17 L) pail, 47.5 gallon (179.8 L) drum
MasterTop SRS 103IN: 4.5 gallon (17 L) pail
MasterTop SRS 100SL: 40 pound (18.1 kg) bag
MasterTop SRS 100HD / Powder Hardener: 2.5 pound (1.1 kg) bottle, 50 pound box
MasterTop PGM 155 Pigment: 10 pound (4.5 kg) pail
MasterTop DE 111FK Flake Blend: 55 pound (25 kg) box

COLOR

See Performance Flooring Color Guide for pigment and flake blend color offerings.

SHELF LIFE

Resins: 2 years when properly stored

STORAGE

Keep stored in cool, dry environment, and out of direct sunlight.

VOC CONTENT

See MasterTop SRS LEED Letter

DESCRIPTION

MasterTop 1841 SRS CF is a methyl-methacrylate (MMA), self-leveling flexible flooring system for use in areas that require a quick curing, decorative floor. The quick installation process makes this flooring system ideal for research facilities, laboratories, public assembly facilities or office buildings where minimal downtime is required. MasterTop 1841 SRS CF is an impervious, seamless flooring system, where dirt and spills will remain on the surface and are easily removed by most regular cleaning procedures. Additionally, MasterTop 1841 SRS CF is a flexible flooring system able to withstand environments with temperature swings or exterior applications. The unique chemistry of the MasterTop 1841 SRS CF system provides a full cure in one hour or less for each component and provides a permanent chemical bond between each coat.

PRODUCT HIGHLIGHTS

- Fully cures in one hour, reducing downtime for a quick return to service
- Seamless, impervious floor that is easy to sanitize, clean and maintain
- UV resistance providing long term color performance
- Decorative flake broadcast provides an aesthetic texture that hides visible dirt
- Excellent chemical resistance for a wide range of applications
- NSF registered for incidental food contact (R2)
- Flexible flooring system able to withstand temperature swings

APPLICATIONS

- Used to resurface and coat concrete floors
- Use where aesthetics are a concern
- Exterior environments subject to freeze/thaw
- Pharmaceutical processing and research areas
- Over de-glazed quarry tile
- Grocery stores
- Food processing facilities
- Public assembly facilities and stadiums

LOCATION

- Interior flooring applications
- Applications subject to the freeze/thaw from exterior environments.

SUBSTRATE

- Over new or existing concrete surfaces. When applying over other substrates, such as metal or tile, contact BASF Technical Service.

TECHNICAL DATA
 TEST DATA

MASTERTOP SRS 41P

PROPERTY	RESULTS	TEST METHODS
Percentage Reactive Resin	100%	
Percentage Solids	100%	
Water Absorption, (%/24 hours)	0.06	ASTM D570
Tensile Strength	3,550 psi (24.5 MPa)	ASTM D638
Elongation @ Break	1.3%	ASTM D638
Tensile Modulus	2.1 x 10 ⁵ psi	ASTM D638
Hardness (Shore D)	75	ASTM D2240
Viscosity	15 – 25 cps	ASTM D2393
Electrical Resistivity	Vol: 2.5 x 10 ¹⁵ ohm/cm Surf: 8 x 10 ¹² ohm	ASTM D257 ASTM D257

MASTERTOP SRS 40TC

PROPERTY	RESULTS	TEST METHODS
Percentage Reactive Resin	100%	
Percentage Solids	100%	
Water Absorption, (%/24 hours)	<0.1%	ASTM D570
Tensile Strength	1,350 psi (9.3 MPa)	ASTM D638
Elongation @ Break	140%	ASTM D638
Hardness (Shore D)	61	ASTM D2240
Viscosity	450 – 550 cps	ASTM D2393

MASTERTOP SRS 71TC

PROPERTY	RESULTS	TEST METHODS
Percentage Reactive Resin	100%	
Percentage Solids	100%	
Water Absorption, (%/24 hours)	0.05	ASTM D570
Tensile Strength	3,555 psi (24.51 MPa)	ASTM D638
Elongation @ Rupture	4%	ASTM D638
Hardness (Shore D)	80	ASTM D2240
Viscosity	45 – 70 cps	ASTM D2393
Taber Abrasion Resistance (mg. Loss, 1000 cycles, CS17 Wheel)	54	ASTM D4060
Electrical Resistivity	Vol: 7.5 x 10 ¹³ ohm/cm Surf: 6.5 x 10 ¹² ohm	ASTM D257 ASTM D257

Chemical Resistance: Please refer to BASF Performance Flooring Chemical Resistance Guide

HOW TO APPLY

Every MasterTop SRS flooring system is a multiple component system that utilizes a methyl-methacrylate (MMA) resin. It is critical that the instructions listed in the Safety Data Sheet and on the product label for every component of the system be read, understood and followed. MMA resins are flammable liquids in their uncured state. Smoking, open flames or sparks should not be permitted during the handling of the product. Explosion safe ventilation must be used during the application to minimize vapor collection in the installation area and to improve overall air quality for the crew. All foodstuffs must be removed during installation of the flooring system.

MasterTop SRS flooring systems are installed by approved contracting firms. The following is only a summary of the installation techniques used by SRS MasterTop SRS approved contractors.

SURFACE PREPARATION

1. Floors must be structurally sound and fully cured a minimum of 28 days. Test floor for vapor drive in accordance with ASTM D 4263, ASTM F 2170 or ASTM F 2420.
2. Repair concrete as necessary. If any patching is required, MasterTop 1817 SRS PC should be mixed and placed according to the MasterTop SRS Installation Guide.
3. Use a commercial degreaser to clean floors of oil, grease and other bond-inhibiting materials.
4. Remove curing and parting compounds and other surface hardeners and floor coatings in accordance with manufacturer's instructions.
5. Mechanical surface profiling is the method of surface preparation for both new and existing floors. Mechanically profile the floor to CSP-4 as described by the International Concrete Repair Institute. Do not use acid etching for surface preparation. Do not use any method that will fracture the concrete.

6. Bond tests should be performed once a small area has been mechanically profiled, so any adjustments can be made to the surface preparation process. Bond tests should be repeated every 500 – 1,000 ft² (46.5 - 93 m²). Please refer to Bond Test Instruction Guide for further information.
7. Cracks wider than 1/16" (1.6 mm) should be "chased out" and opened during surface preparation. Any existing joints should be treated according to project specifications. Please refer to Joint Repair Guide for further information.
8. Areas around drains and other floor fixtures need to be ground and/or chipped to a depth between 1/2" – 3/4" (12.7 - 19 mm) and tapered back 3" – 6" (7.6 - 15.2 cm) away from drain (Refer to MasterTop SRS Detail Drawing 3.1).
9. Termination points should be saw cut to a depth of 1/4" (6.4 mm) and tapered back (Refer to MasterTop SRS Detail Drawing 3.2).

MIXING

(Refer to SRS MasterTop SRS Mixing Chart for exact batch sizes and measurements)

MASTERTOP SRS 41P PRIMER

Measure resin and MasterTop SRS 103IN into pail and add proper amount of powder hardener. Mix with drill mixer for 15 – 30 seconds or until the powder hardener is completely dissolved.

MASTERTOP SRS 40TC SL OVERLAY

Measure resin and pigment into a 5 gallon pail. Add 1 bag of MasterTop SRS 100SL powder and mix using a spiral mixing blade for 40 – 50 seconds, until a homogenous mixture is obtained. Add proper amount of powder hardener and mix for an additional 20 seconds.

MASTERTOP SRS 71TC TOP COAT

Measure resin into pail and add proper amount of powder hardener. If desired, you can mix in the proper amount of pigment. Mix with drill mixer for 15 – 30 seconds or until the powder hardener is completely dissolved. NOTE: After mixing, apply immediately. There will be 7 to 15 minutes of working time, dependent on temperature.

APPLICATION

PRIMER

Apply the properly mixed MasterTop SRS 41P resin to the properly repaired concrete or properly prepared aged coating at approximately 100 ft² (9.3 m²) per batch. Allow primer to cure tack-free to an even, satin-like gloss and re-prime any dry spots.

COVE BASE

If a cove base is to be installed, mix and apply according to the SRS MasterTop SRS "Cove Base Application Guide". Install cove base prior to installation of overlay coat.

SCRATCH COAT

Any rough areas or depressions less than 1/4" (6.4 mm) should receive a scratch coat of MasterTop SRS 40TC SL to smooth and level these areas. Any drips or ridges over 1/8" (3.2 mm) should be ground or sanded smooth. Allow to cure.

OVERLAY COAT

Apply the properly mixed MasterTop SRS 40TC SL overlay coat at 40 ft² (3.71 m²) per batch, at 1/8" (3.2 mm) thickness.

AGGREGATE BROADCAST

Immediately following overlay coat installation, broadcast aggregate into wet material. Even broadcast is best achieved by throwing handfuls of broadcast media towards ceiling and letting it "rain down" on surface. Broadcast until no wet spots are apparent on floor. Allow overlay coat material to cure. Remove excess by sweeping with a medium stiff broom. Follow with a thorough vacuum or blow down to remove all remaining excess aggregate.

TOP COAT (1ST COAT)

Apply the properly mixed MasterTop SRS 71TC topcoat at approximately 80 – 100 ft² (7.4 - 9.3 m²) per batch. Allow to cure.

TOP COAT (2ND COAT)

Apply second coat of properly mixed MasterTop SRS 71TC at approximately 100 – 120 ft² (9.3 – 11.1 m²) per batch. Allow to cure.

DRYING TIME

All components of the MasterTop 1841 SRS CF flooring system fully cure within one hour.

CLEAN UP

Clean tools as needed with inhibited MMA, acetone, ethyl acetate or similar solvents. Collect and dispose of all site wastes.

MAINTENANCE

Regular cleaning and maintenance will prolong the life of all polymer flooring systems, enhance their appearance and reduce any tendency to retain dirt. Follow the BASF Performance Flooring Protection and Maintenance Guide to maximize the life of the floor.

FOR BEST PERFORMANCE

- Not for use at application temperatures over 90° F (32° C).
- Not for use in areas exposed to strong solvents (consult BASF Technical Service).
- Install at recommended thickness to ensure proper curing and leveling.
- Topcoat must be back-rolled immediately to ensure uniform finish.
- Each application must be completely cured prior to the next application.
- Protect or remove food items prior to application to avoid any possible contamination.
- Use clean pails when mixing to avoid the possibility of improper curing.
- Proper air flow is critical to curing MMA materials. The use of fans is mandatory where air flow is restricted.
- Apply a bond test every 500 – 1,000 ft² prior to floor installation.
- BASF flooring specialists are available to assist you in the selection of the proper flooring system. Call 1-800-243-6739 for in-house and field technical assistance.
- Make certain the most current versions of product data sheet and SDS are being used; visit www.master-builders-solutions.BASF.us to verify the most current versions.
- Proper application is the responsibility of the user. Field visits by BASF personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

HEALTH, SAFETY AND ENVIRONMENTAL

Health, Safety and Environmental Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting www.master-builders-solutions.basf.us, e-mailing your request to basfbcst@basf.com or calling 1(800)433-9517. Use only as directed. **For medical emergencies only, call ChemTrec 1(800)424-9300.**

LIMITED WARRANTY NOTICE

Every reasonable effort is made to apply BASF exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, BASF MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS, and BASF shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the BASF Technical Manager.

This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, BASF disclaims all CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. BASF SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS)

OF ANY KIND. BASF reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

FOR PROFESSIONAL USE ONLY. NOT FOR SALE TO OR USE BY THE GENERAL PUBLIC.

BASF Corporation
Constructions Systems

889 Valley Park Drive, Shakopee, MN 55379
www.master-builders-solutions.basf.us

Customer Service 1(800)433.9517
Technical Service 1(800)243.6739

